



# Rofalin Acrylic

Weather protection paint for wood and other substrates in indoor and outdoor areas



Colour	Availability					
		Quantity per pallet	672	200	96	30
	Size / Quantity	0,75 l	2,5 l	5 l	10 l	20 l
	Type of container	Tin bucket	Tin bucket	Tin bucket	Tin bucket	Tin bucket
	Container code	01	03	05	10	20
	<b>Art. no.</b>					
anthracite grey (RAL 7016)	2323		■	■	■	
light grey (RAL 7035)	2324			■	■	
fir green (RAL 6009)	2325			■		
moss green (RAL 6005)	2326		■	■		
white (RAL 9016)	2330	■	■	■	■	■
grey	2332			■		
dark brown	2334			■		
black	2336			■		
special colours*	2343		■	■	■	■
Base A	015020	■	■	■	■	■
Base C	015022	■	■	■	■	■

\*Minimum order quantity 5 l

## Application rate

Approx. 80 - 100 ml/m<sup>2</sup> per coat

If pre-treated with Aqua AG-26 Universal Primer (for light colours): 1 x 100 ml/m<sup>2</sup>



See application examples for substrate-specific configuration

## Range of use



- For use on interior and exterior wood
- Wood building elements with limited dimensional stability, e.g. folding shutters, matchboarding, summerhouses
- Wood building elements with no dimensional stability: e.g. fences, framework, carports, planking
- Zinc roof gutters and zinc sheet metal
- Many other different substrates
- Stable old coatings such as alkyd, acrylate, powder coatings and PUR lacquers
- Do not apply to freshly impregnated wood. Observe fixation time.
- When applying to chairs, benches etc. apply an additional protective coat of Aqua MSL-45/sm clear UV+ (7130) to prevent abrasion of pigments.
- For use by professionals

## Property profile



- Highly opaque
- Does not flake
- Alkali-resistant, including when used on mineral substrates
- Weatherproof and moisture-regulating
- Low solvent, mild odour
- Quick drying
- Scrub-proof
- All colours are mixable with one another
- Brilliant, pure, intensive colours have a lower hiding power due to their pigments. We recommend fully pre-coating such areas with a matching coloured primer if using critical colours.



**Characteristic data of the product**

Density (20 °C)	Approx. 1.15 - 1.24 g/cm <sup>3</sup>
Viscosity (20 °C)	Approx. 2700 mPa s
Odour	Weak, characteristic
Degree of gloss	Matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

**Certificates**

- [DIN EN 71-3 "Migration of certain elements"](#)

**Additional information**

- [Sustainability Data Sheet](#)
- [Colour chart](#)

**Possible system products**

- [Induline SW-910 \(3777\)](#)
- [Aqua AG-26 Universal Primer \(7147\)](#)
- [Aqua HSL-35/m Premium Wood Protection Stain 3in1\\* \(7120\)](#)
- [Primer Hydro HF \(0725\)](#)
- [Primer Hydro F \(2842\)](#)
- [Sealing Primer \(3440\)](#)

\*Use biocidal products carefully.

Always read the label and product information before use.

**Preparation**

■ **Substrate requirements**

Wood building elements with limited or no dimensional stability: wood moisture content max. 18%

■ **Substrate preparation**

Thoroughly remove any dirt, grease and non-adhering old coatings.

**Wood substrates:**

Sand grey and weathered wood surfaces down to sound, bright wood.

Remove loose and torn knots as well as resin that bleeds and clean with a suitable product (e.g. Remmers thinner & brush cleaner).

Exterior wood that is to be protected against rot and blue stain and/or wood-destroying insects should be pre-treated with a suitable wood preservative\* [see system products]. (\*Use biocides safely. Always read the label and product information before use.)

Observe BFS Code of Practice No. 18 "Coatings on Wood and Wooden Working Materials in Outdoor Areas".

To prevent bleeding of substances in the wood, apply a primer coat of Aqua AG-26 Universal Primer when using this product in white or light colours.

To avoid bleeding of substances in the wood into adjoining building elements (e.g. infilling in framework areas), treat the wood all round.

Old weathered carbolineum coatings can only be coated with dark colours. Always test first with a trial coating.

**Zinc (galvanised steel):**

Clean with an ammonium-based wetting agent, using an abrasive pad. Observe BFS Code of Practice No. 5.

Pre-treat with Aqua AG-26 Universal Primer if the substrate is exposed to increased mechanical stresses.

**Mineral substrates:**

Thoroughly remove algae and moss from old fibrated cement surfaces. Allow the substrate to dry fully.

Repair damaged render.

The substrate must be stable, dry, clean, free from dust and cracks (except hairline cracks), and free from harmful salts. Completely remove any non-load-bearing old coatings. Prime stable mineral substrates and sanding but firmly adhering substrates with Primer Hydro HF.

**Directions**



■ **Conditions for use**

Temperature of the material, air and substrate: from min. +5 °C to max. +25 °C.

Stir well.

Apply with a brush, roller or by spraying.

Observe the waiting times between coats.

See application examples for substrate-specific set-up.

Airmix spraying: nozzle size: 0.28 - 0.33 mm, material pressure: 100 - 130 bar,

atomiser air pressure: 2.0 - 2.5 bar.

Airless spraying: nozzle size 0.28 - 0.33 mm, material pressure: 120 - 150 bar

**Tips on use**



Before coating technically modified woods and wood-based materials, apply the product to a trial surface and conduct a suitability test on the desired area of use.

If using white or light colours, apply 2 primer coats of Aqua AG-26 Universal Primer.

The colour shown on the sample does not appear until the material has dried.

Paint-on-paint contact, e.g. stacking, should be avoided.

Do not use on wood impregnated with boron salts.

Ensure sufficient ventilation when applying indoors.

■ **Drying**



2 - 4 hours at 20 °C and 65% relative humidity.

Exterior wood should be protected from rain for at least 4 hours after coating (danger of washing off).

Low temperatures, poor ventilation and high humidity delay drying.

■ **Thinning**

Dilute with water if necessary.

**Application examples**

■ **Substrate-specific set-up**

Application examples	Impregnation	Primer coat	Intermediate coat	Finishing coat
<b>Wood substrates:</b> Untreated wood, old weathered wood substrates, renovation coats on dispersion paints, varnishes and wood preservation stains	If necessary, using Aqua IG-15 Impregnation Primer IT (in outdoor areas only)	Aqua AG-26 Universal Primer or Rofalin Acrylic	Aqua AG-26 Universal Primer or Rofalin Acrylic	Rofalin Acrylic
<b>Zinc (galvanised steel):</b> Zinc, galvanised steel and rigid PVC, renovation coats on old coatings	--	Aqua AG-26 Universal Primer (for higher requirements)	Rofalin Acrylic	Rofalin Acrylic
<b>Mineral substrates:</b> Fibre-reinforced cement, weathered	--	1-2 x Primer Hydro HF	Rofalin Acrylic	Rofalin Acrylic
Fair-faced concrete, non-porous concrete	--	Primer Hydro HF	Rofalin Acrylic diluted with 10% water	Rofalin Acrylic
Old renders, exterior (sanding renders, stable renders)	--	Primer Hydro HF	Rofalin Acrylic diluted with 10% water	Rofalin Acrylic
Stable renders, interior (gypsum plasters, lime mortar plaster, fair-faced masonry)	--	Rofalin Acrylic diluted with 10% water	--	Rofalin Acrylic
Renovation coats on stable old dispersion paint coats, synthetic renders	--	--	Rofalin Acrylic diluted with 10% water	Rofalin Acrylic
Gypsum plasterboard	--	Primer Hydro F	Rofalin Acrylic	Rofalin Acrylic
Wallpaper, coarse fibres etc.	--	Rofalin Acrylic	--	Rofalin Acrylic

**Notes**

DIN EN 71-3 "Migration of certain elements":

This product complies with the limits for the migration of heavy metals to children's toys according to DIN EN 71-3 and thus fulfils one of several further requirements for the safety of children's toys according to the EU "Toy Directive" (2009/48/EC).

On planed larch and softwoods with a high resin content, the coating may have reduced adhesion and resistance to weathering. This is especially the case on horizontal year rings, knots and areas of winter growth that are high in resin. Maintenance and renovation must be carried out more frequently on these surfaces. The only remedy for this is pre-weathering or very coarse sanding (P80). If these wood types are rough-sawn, considerably longer maintenance and renovation intervals are to be expected.



Observe the regulations concerning design principles for wood protection.  
Do not use on horizontal surfaces without drainage slopes and without edge radius, avoid accumulated moisture.

**Tools / Cleaning**




Brush with synthetic bristles, flat brush, foam roller, Airmix/airless spraying equipment  
Clean tools immediately after use with water and detergent.  
Ensure that any residue from cleaning is disposed of correctly.

**Remmers tools**

- > **Flächenstreicher (4540)**
- > **Farbrolle FC (4913)**
- > **Rollerbügel (4449)**
- > **Pro nylon roller (5045)**
- > **Heizkörperpinsel (4541)**

**Storage / Shelf life**



At least 36 months in unopened, original containers stored cool, dry and protected from frost.

**Safety data / Regulations**

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

**Disposal**

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

**Biocidal Products Regulation**

Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!

**VOC content as per the "Decopaint" Directive (2004/42/EC)**

EU limit value for the product (cat A/d): max. 130 g/l (2010).  
This product contains < 130 g/l VOC.

VOC	
Kat.	A/d
2010:	130g/l
max.:	130g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.